

MATERIAL NUMBER 1.5637 · CLASS 1.5

3.5Ni355

Material no. 1.5637

also listed as 10Ni14


Chemical composition, mechanical and physical property values, and 31 standard designations from 10 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 31 in 10 regions	PROPERTY VALUES 8 on file
------------------------------	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Cr, Mo.

Mechanical properties

5 values across 1 conditions

NORMALIZED	REH N/mm ²	RM N/mm ²	A %
≤ 30	355	–	–
30 – 50	345	–	–
50 – 80	335	–	–
≤ 80	–	490–640	20–22

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

31 designations · 6 documented as identical

United States		9	Japan		4
K31718	This grade's own name	uns	G3127 gr. SL3N255		jis
K31918	This grade's own name	uns	G3127 gr. SL3N440		jis
K32018	This grade's own name	uns	G3127 gr. SL5N590		jis
K32025	This grade's own name	uns	G3464 gr. STBL450		jis
K41583		uns			
A350-LF3		aisi-sae	United Kingdom		3
A 333 Grade 3		astm	1501-503-690		bs
A 350 Grade LF3		astm	BS1501 Gr 503		bs
A 420 Grade WPL3		astm	BS3603 gr. 503LT		bs
Europe		4	Spain		2
1.5637		din-en	A-152		une
10Ni14	This grade's own name	din-en	F.152		une
12Ni14	This grade's own name	din-en			
X12Ni14		din-en	China		2
			07Ni5DR		gb
			08Ni3DR		gb
France		4	International		1
12N14		afnor	X9Ni5		iso
12NJ14		afnor			
3.5Ni355		afnor	Czechia		1
Z10N05		afnor	16329VN		csn
			Hungary		1
			AH80		msz

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 3.5Ni355

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE

[View the material page](#)

GRADE SEARCH

[Search all grades](#)

MATERIAL NO.

1.5637

ISSUED

Aug 20, 2026