

MATERIAL NUMBER 1.0389 · CLASS 1.0

3CT

Material no. 1.0389


also listed as DD 14

Chemical composition, mechanical and physical property values, and 3 standard designations from 3 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 3 in 3 regions	PROPERTY VALUES 5 on file
--	---	-------------------------------------

Chemical composition

Mass fraction in %



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Si, Ni, Cr, Mo.

Mechanical properties

6 values across 1 conditions

CONDITION · DIMENSION	REH N/mm ²	A80 % · Lo = 80 mm	A % · Lo = 5,65 √So
1–2	170–310	–	–

CONDITION · DIMENSION	REH N/mm ²	A80 % · Lo = 80 mm	A % · Lo = 5,65 √So
1 – 1.5	–	30	–
1.5 – 2	–	31	–
2 – 11	170–290	–	–
2 – 3	–	32	–
3 – 11	–	–	36

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

3 designations · 1 documented as identical

Europe	1	Czechia	1
DD 14 This grade's own name	din-en	11305	csn
France	1		
3CT	afnor		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 3CT

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.0389	Aug 20, 2026