

MATERIAL NUMBER 1.5634 · CLASS 1.5

75Ni8RR

Material no. 1.5634

also listed as 75Ni8

Chemical composition, mechanical and physical property values, and 2 standard designations from 2 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 2 in 2 regions	PROPERTY VALUES 9 on file
------------------------------	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Mechanical properties

4 values across 3 conditions

SOFT ANNEALED	RM N/mm ²	A80 %
0.3 – 3	680	13
QUENCHED AND TEMPERED		RM N/mm ²
0.3 – 3		1200–1800
SOFT ANNEALED		HV
Soft annealed		210

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

2 designations · 1 documented as identical

Europe	1	France	1
75Ni8 This grade's own name	din-en	75Ni8RR	afnor

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 75Ni8RR

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.5634	Aug 20, 2026