

MATERIAL NUMBER 1.0548 · CLASS 1.0

E315C

Material no. 1.0548

also listed as H 320 LA

Chemical composition, mechanical and physical property values, and 6 standard designations from 4 regions.

DENSITY

7.85 g/cm³

OTHER DESIGNATIONS

6 in 4 regions


PROPERTY VALUES

9 on file


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

3 values across 1 conditions

CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A %
Sheet/Strip	490	295	23–24

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

6 designations · 3 documented as identical

Europe	3	France	1
H 320 LA This grade's own name	din-en	E315C	afnor
HC 340 LA This grade's own name	din-en		
ZStE 340 This grade's own name	din-en	Japan	1
		SPFC490	jis
United States	1		
Gr.50	aisi-sae		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about E315C

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.0548

ISSUED

Aug 20, 2026