

MATERIAL NUMBER 1.2581 · CLASS 1.2

Z30WCV9

Material no. 1.2581

also listed as X30WCrV9-3

Chemical composition, mechanical and physical property values, and 33 standard designations from 18 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 33 in 18 regions	PROPERTY VALUES 16 on file
--	---	--------------------------------------

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 86.9 % ● W — 9 % ● Cr — 2.9 % ● V — 0.4 % ● Traces & impurities · 0.9 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Mechanical properties

9 values across 4 conditions

CONDITION · DIMENSION		HB			HRC
Annealed		241			—
Quenched and tempered		—			48
SOFT ANNEALED					HB
Soft annealed					241
CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A5 %	Z %	KCU kJ/m ²
Steel	1530	1390	12	36	200
CONDITION · DIMENSION					HB
(annealing)					241

Physical properties

8 values

CONDITION · DIMENSION	E GPa	LAMBDA W/(m·K)	RHO_EL nΩ·m	
20	224	–	–	
100	218	25	250	
200	211	27	200	
300	204	29	170	
400	196	40	140	
500	187	46	120	
600	177	50	–	
PROPERTY	VALUE		UNIT	
Density	7.85		g/cm ³	
Transformation point Ac1	800		°C	
Transformation point Ac3	850		°C	
Transformation point Ar3	750		°C	
Transformation point Ar1	690		°C	

Technological properties

PROPERTY	VALUE	UNIT
Weldability	is not used.	

PROPERTY	VALUE	UNIT
Flake sensitivity	predisposed	
Temper brittleness	predisposed	

Heat treatment

3 regimes

STEP	TEMPERATURE	MEDIUM
Quenching	Temperature not stated	—
Quenching	1070–1125 °C	Oil
Annealing	Temperature not stated	—

Designations across standards

33 designations · 3 documented as identical

Spain	4	Italy	2
F.5320	une	X28W09KU	uni
F.5323	une	X30WCrV9-3KU	uni
WCrV9	une		
X30WCrV9	une	Czechia	2
		19721	csn
United States	3	19830	csn
T20821 This grade's own name	uns		
H21 This grade's own name	aisi-sae	Poland	2
T20821	aisi-sae	WWV	pn
		WWW	pn
Europe	2		
1.2581	din-en	Bulgaria	2
X30WCrV9-3 This grade's own name	din-en	3Ch2B8F	bds
		X30WCrV9-3	bds
United Kingdom	2		
2581	bs	Austria	2
BH21	bs	BOHLERW100	onorm
		W100	onorm
France	2		
X30WCrV9	afnor	International	1
Z30WCV9	afnor	X30WCrV9-3	iso
China	2	Japan	1
30WCrV9	gb	SKD5	jis
3Cr2W8V	gb		
		Slovakia	1
Russia / CIS	2	19 721	stn
3KH2V8F	gost		
3X2B8Φ	gost	Serbia	1
		Č.6451	srps

Romania	1	South Korea	1
30VCrW85	stas	STD5	ks

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about Z30WCV9

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.2581	Aug 20, 2026