

MATERIAL NUMBER 1.4941 · CLASS 1.4

Z6CNT18-10B

Material no. 1.4941

also listed as X6CrNiTiB18-10


Chemical composition, mechanical and physical property values, and 5 standard designations from 3 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.85 g/cm ³	5 in 3 regions	9 on file


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

5 designations · 4 documented as identical

Europe	2	United States	2
X6CrNiTiB18-10	This grade's own name din-en	S32109	This grade's own name uns
X8CrNiTi18-10	This grade's own name din-en	321H	This grade's own name aisi-sae
		France	1
		Z6CNT18-10B	afnor

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about Z6CNT18-10B

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.4941	Aug 20, 2026