

MATERIAL NUMBER 2.4636 · CLASS 2.4

687

Material no. 2.4636

also listed as NiCo15Cr15MoAlTi

Chemical composition, mechanical and physical property values, and 3 standard designations from 3 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.85 g/cm ³	3 in 3 regions	16 on file

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 54.3 % ● Cr — 15 % ● Co — 15 % ● Al — 5 % ● Traces & impurities · 10.7 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



0.01 %0.1 %1 %10 %100 %

The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni.

Physical properties1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards3 designations · 1 documented as identical

Europe	1	France	1
NiCo15Cr15MoAlTi	This grade's own name din-en	NCKD 20 AT	afnor
United States	1		
687	aisi-sae		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 687

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	2.4636	Aug 20, 2026