

MATERIAL NUMBER EN-JL1040

C1.35B

Material no. EN-JL1040

also listed as EN-GJL-250

Chemical composition, mechanical and physical property values, and 36 standard designations from 22 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 36 in 22 regions	PROPERTY VALUES 2 on file
-----------------------	--	------------------------------

Chemical composition	Mass fraction in %
No chemical composition is on file for this material number.	

Predicted transformation temperatures
Not enough recorded composition to predict a transformation temperature for this grade — missing: C, Mn, Si, Ni, Cr, Mo.

Mechanical properties		2 values across 1 conditions
CONDITION · DIMENSION	RM N/mm²	HB
Casting, GOST 1412-85	250	–
GOST 1412-85	–	156–260

Physical properties					2 values
CONDITION · DIMENSION	RHO g/cm³	E GPa	ALPHA 10^-6/K	LAMBDA W/(m·K)	CP J/(kg·K)
20	7.2	100	–	50	–
100	–	–	10	–	500

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³
nu	0.26	

Designations across standards

36 designations · 3 documented as identical

United States	5	Spain	1
F12401 This grade's own name	uns	FG25	une
A48-40B	aisi-sae		
C1.35B	aisi-sae	International	1
No 35 B	aisi-sae	250	iso
No.35	aisi-sae		
United Kingdom	3	China	1
250	bs	HT250	gb
260	bs	Italy	1
Grade 260	bs	G25	uni
Sweden	3	Czechia	1
0125	ss	422425	csn
0125-00	ss		
0125	ss	Latin America	1
Europe	2	FG250	copant
EN-GJL-250 This grade's own name	din-en	Hungary	1
GG-25 This grade's own name	din-en	OV25	msz
France	2	Romania	1
FGL250	afnor	FC250	stas
Ft 25 D	afnor		
Japan	2	Australia / New Zealand	1
FC25	jis	T260	as-nzs
FC250	jis	Bulgaria	1
Russia / CIS	2	Vch25	bds
SCH25	gost	Belgium	1
C425	gost	FGG25	nbn
Poland	2	Netherlands	1
Z125	pn	GG25	nen
ZI250	pn	Taiwan	1
Austria	2	FC250	cns
GG25	onorm		
GG250	onorm		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about C1.35B

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE
View the material page

GRADE SEARCH
Search all grades

MATERIAL NO.
EN-JL1040

ISSUED
Aug 20, 2026