

MATERIAL NUMBER 1.3207 · CLASS 1.3

T11348

Material no. 1.3207

also listed as HS10-4-3-10


Chemical composition, mechanical and physical property values, and 20 standard designations from 15 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
8.23 g/cm ³	20 in 15 regions	15 on file


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni.

Mechanical properties

7 values across 3 conditions

SOFT ANNEALED					HB
Soft annealed					302
CONDITION · DIMENSION	RM N/mm²	RE N/mm²	A5 %	Z %	KCU kJ/m²
As-delivered state	960	540	7	10	80
CONDITION · DIMENSION					HB
(annealing) , GOST 19265-73					285

Physical properties

5 values

CONDITION · DIMENSION	RHO g/cm³	E GPa	LAMBDA W/(m·K)	
20	8.3	229	–	
100	–	–	25	
200	–	–	27	
300	–	–	28	
400	–	–	29	
500	–	–	30	
600	–	–	31	
700	–	–	32	
900	–	–	32	
PROPERTY	VALUE		UNIT	
Density	8.23		g/cm³	
Transformation point Ac1	800		°C	
Transformation point Ac3	840		°C	
Transformation point Ar3	790		°C	
Transformation point Ar1	750		°C	

Designations across standards

20 designations · 2 documented as identical

Russia / CIS	4	Sweden	1
R9M4K8	gost	2736	ss
R9M4K8-MP	gost	Czechia	1
Д1102-МП	gost	19861	csn
P9M4K8	gost	Slovakia	1
Europe	2	19 861	stn
HS10-4-3-10 This grade's own name	din-en	Serbia	1
S10-4-3-10 This grade's own name	din-en	Č.9683	srps
France	2	Poland	1
HS10-4-3-10	afnor	SK10V	pn
Z130WKCDV	afnor	Hungary	1
United States	1	R14	msz
T11348	aisi-sae	Bulgaria	1
United Kingdom	1	R9M4K8	bds
BT42	bs	Austria	1
Japan	1	S700	onorm
SKH57	jis		
Italy	1		
HS10-4-3-10	uni		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about T11348

[Start an enquiry](#)

Quotation, availability, mill certificate or a technical question — directly on the material page.

DATASHEET ONLINE

[View the material page](#)

GRADE SEARCH

[Search all grades](#)

MATERIAL NO.

1.3207

ISSUED

Aug 20, 2026