

MATERIAL NUMBER 1.4933 · CLASS 1.4

5719

Material no. 1.4933

also listed as S64152


Chemical composition, mechanical and physical property values, and 8 standard designations from 3 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 8 in 3 regions	PROPERTY VALUES 11 on file
--	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no

transformation temperature is predicted here.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

8 designations · 2 documented as identical

United Kingdom		5	United States		2
S151	bs		S64152	This grade's own name	uns
S159	bs		XM-32	This grade's own name	aisi-sae
S159A	bs		United States / Aerospace		1
S159D	bs				
S191	bs		5719		ams

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 5719

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.4933	Aug 20, 2026