SteelEquivalents.com

Material datasheet
As of Aug 20, 2026

MATERIAL NUMBER 2.4964 · CLASS 2.4

5796

Material no. 2.4964

also listed as CoCr20W15Ni

Chemical composition, mechanical and physical property values, and 8 standard designations from 3 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
9.1 g/cm³	**8** in 3 regions	**11** on file

Chemical composition

Mass fraction in %

What this alloy is

Iron — the balance, never listed by a standard — 52.5 % · Cr — 20 % · W — 15 % · Ni — 10 % · Traces & impurities · 2.5 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	9.1	g/cm³

Designations across standards

8 designations · 3 documented as identical

United States / Aerospace (4)

5537	ams
5759	ams
5796	ams
5797	ams

United States (3)

R30605 This grade's own name	uns
670 This grade's own name	aisi-sae
F90	astm

Europe (1)

CoCr20W15Ni This grade's own name	din-en

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 5796

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	2.4964	Aug 20, 2026