

# A266

Chemical composition, mechanical and physical property values, and 2 standard designations from 2 regions.

## OTHER DESIGNATIONS

**2** in 2 regions

## PROPERTY VALUES

**10** on file

## Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 97.8 % ● Mn — 0.9 % ● Ni — 0.3 % ● Si — 0.3 % ● Traces & impurities · 0.8 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



## Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

## Heat treatment

2 regimes

STEP

TEMPERATURE

MEDIUM

source joins the operations with + / procedural order

| STEP                                                  | TEMPERATURE            | MEDIUM |
|-------------------------------------------------------|------------------------|--------|
| Normalizing                                           | Temperature not stated | —      |
| Quenching                                             | Temperature not stated | —      |
| Tempering                                             | Temperature not stated | —      |
| source joins the operations with + / procedural order |                        |        |
| Normalizing                                           | Temperature not stated | —      |
| Quenching                                             | Temperature not stated | —      |
| Tempering                                             | Temperature not stated | —      |

Designations across standards

2 designations · 1 documented as identical

|               |      |                                         |    |
|---------------|------|-----------------------------------------|----|
| United States | 1    | China                                   | 1  |
| A266          | astm | 25Mn <span>This grade's own name</span> | gb |

**Note on use.** The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

### Enquiry about A266

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

|                        |                   |              |              |
|------------------------|-------------------|--------------|--------------|
| DATASHEET ONLINE       | GRADE SEARCH      | MATERIAL NO. | ISSUED       |
| View the material page | Search all grades | —            | Aug 15, 2026 |