

MATERIAL NUMBER 2.4660 · CLASS 2.4

B468

Material no. 2.4660

also listed as NiCr20CuMo


Chemical composition, mechanical and physical property values, and 15 standard designations from 4 regions.

DENSITY 8.1 g/cm ³	OTHER DESIGNATIONS 15 in 4 regions	PROPERTY VALUES 12 on file
---	--	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	8.1	g/cm ³

Designations across standards

15 designations · 2 documented as identical

United States	10	International	2
N08020 This grade's own name	uns	FeNi35Cr20Cu4Mo2	iso
A240	astm	NW8020	iso
B 366	astm		
B 463	astm	China	2
B 464	astm	H08020	gb
B 473	astm	NS1403	gb
B462	astm		
B468	astm	Europe	1
B729	astm	NiCr20CuMo This grade's own name	din-en
B775	astm		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about B468

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	2.4660	Aug 20, 2026