

MATERIAL NUMBER 1.0723 · CLASS 1.0

210A15

Material no. 1.0723

also listed as 15 S 20

Chemical composition, mechanical and physical property values, and 5 standard designations from 4 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 5 in 4 regions	PROPERTY VALUES 6 on file
--	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

5 designations · 2 documented as identical

Europe	2	Spain	1
15 S 20	This grade's own name din-en	F.210F	une
15 S 22	This grade's own name din-en		
United Kingdom	1	Sweden	1
210A15	bs	1922	ss

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 210A15

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.0723	Aug 20, 2026