

MATERIAL NUMBER 1.0973 · CLASS 1.0

40/30

Material no. 1.0973

also listed as QStE 300 N


Chemical composition, mechanical and physical property values, and 3 standard designations from 2 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.85 g/cm ³	3 in 2 regions	10 on file


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

2 values across 1 conditions

CONDITION · DIMENSION	A80 % · Lo = 80 mm	A % · Lo = 5,65 √So
≤ 3	22	–
≥ 3	–	27

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

3 designations · 2 documented as identical

Europe	2	United Kingdom	1
QStE 300 N This grade's own name	din-en	40/30	bs
S315NC This grade's own name	din-en		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 40/30

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.0973	Aug 20, 2026