

MATERIAL NUMBER 1.4317 · CLASS 1.4

425 C 12

Material no. 1.4317

also listed as G-X 5 CrNi 13 4


Chemical composition, mechanical and physical property values, and 8 standard designations from 4 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 8 in 4 regions	PROPERTY VALUES 11 on file
--	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no

transformation temperature is predicted here.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

8 designations · 3 documented as identical

Europe	2	United Kingdom	2
G-X 5 CrNi 13 4	This grade's own name din-en	425 C 11	bs
GX4CrNi13-4	This grade's own name din-en	425 C 12	bs
United States	2	Japan	2
J91540	This grade's own name uns	SCS 6	jis
J91540	aisi-sae	SCS 6X	jis

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 425 C 12

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.4317

ISSUED

Aug 20, 2026