

MATERIAL NUMBER 1.0167 · CLASS 1.0

11379

Material no. 1.0167

also listed as S235JR


Chemical composition, mechanical and physical property values, and 8 standard designations from 5 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 8 in 5 regions	PROPERTY VALUES 7 on file
-----------------------	--------------------------------------	------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element’s raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Si, Ni, Cr, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

8 designations · 2 documented as identical

Brazil	3	United Kingdom	1
NBR 6648 CG26	abnt	Gr 40A	bs
NBR 6650 CF26	abnt	Czechia	1
NBR 7007 MR250	abnt	11379	csn
Europe	2	South Africa	1
S235JR This grade's own name	din-en	240 WA	sans
S235JRG2Cu This grade's own name	din-en		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 11379

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.0167

ISSUED

Aug 20, 2026