

MATERIAL NUMBER 1.5523 · CLASS 1.5

12 122 TŽ

Material no. 1.5523

also listed as 19MnB4

Chemical composition, mechanical and physical property values, and 6 standard designations from 4 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.85 g/cm ³	6 in 4 regions	8 on file

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 98.3 % ● Mn — 1 % ● Si — 0.4 % ● C — 0.2 % ● Traces & impurities · 0.1 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

3 values across 1 conditions

QUENCHED AND TEMPERED	RM N/mm ²	A %	Z %
≤ 16	800–950	14	52

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

6 designations · 4 documented as identical

United States	3	France	1
H15211 This grade's own name	uns	20MB5	afnor
15B21H This grade's own name	aisi-sae		
15B21RH This grade's own name	aisi-sae	Czechia	1
		12 122 Tž	csn
Europe	1		
19MnB4 This grade's own name	din-en		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 12 122 Tž

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.5523	Aug 20, 2026