

MATERIAL NUMBER 1.8161 · CLASS 1.8

15 261

Material no. 1.8161

also listed as 58CrV4


Chemical composition, mechanical and physical property values, and 7 standard designations from 5 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 7 in 5 regions	PROPERTY VALUES 8 on file
--	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

7 designations · 1 documented as identical

Russia / CIS	3	Czechia	1
50ChFA	gost	15 261	csn
50HFA	gost		
50KhFA	gost	Poland	1
		50HF	pn
Europe	1		
58CrV4	This grade's own name din-en	Serbia	1
		Č.4831	srps

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 15 261

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.8161	Aug 20, 2026