

MATERIAL NUMBER 1.2082 · CLASS 1.2

19 434

Material no. 1.2082

also listed as X21Cr13


Chemical composition, mechanical and physical property values, and 4 standard designations from 3 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 4 in 3 regions	PROPERTY VALUES 7 on file
------------------------------	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element’s raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

4 designations · 1 documented as identical

Czechia	2	Europe	1	
17 022	csn	X21Cr13	This grade's own name	din-en
19 434	csn	United States	1	
		420	aisi-sae	

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 19 434

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.2082	Aug 20, 2026