

MATERIAL NUMBER 1.2605 · CLASS 1.2

19 555

Material no. 1.2605

also listed as X35CrWMoV5

Chemical composition, mechanical and physical property values, and 7 standard designations from 5 regions.

DENSITY

7.85 g/cm³

OTHER DESIGNATIONS

7 in 5 regions

PROPERTY VALUES

10 on file

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 90 % ● Cr — 5.1 % ● Mo — 1.4 % ● W — 1.4 % ● Traces & impurities · 2.1 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni.

Mechanical properties

3 values across 2 conditions

CONDITION · DIMENSION	HB	HRC
Annealed	229	–
Quenched and tempered	–	48
SOFT ANNEALED		HB
Soft annealed		229

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

7 designations · 3 documented as identical

United States	2	Europe	1
T20812 This grade's own name	uns	X35CrWMoV5 This grade's own name	din-en
H12 This grade's own name	aisi-sae	International	1
Czechia	2	X35CrMoV5	iso
19 555	csn	Japan	1
19 555 PH	csn	SKD62	jis

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 19 555

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.2605	Aug 20, 2026