

MATERIAL NUMBER 1.6228 · CLASS 1.6

14NiMn6

Material no. 1.6228


Chemical composition, mechanical and physical property values, and 3 standard designations from 2 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 3 in 2 regions	PROPERTY VALUES 8 on file
--	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Cr, Mo.

Mechanical properties

5 values across 1 conditions

NORMALIZED	REH N/mm ²	RM N/mm ²	A %
≤ 30	355	—	—
30 – 50	345	—	—
50 – 80	335	—	—
≤ 80	—	470–640	20–22

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

3 designations · 2 documented as identical

Europe	2	France	1
14NiMn6	This grade's own name din-en	1.5Ni355	afnor
15NiMn6	This grade's own name din-en		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 14NiMn6

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.6228	Aug 20, 2026