

MATERIAL NUMBER 1.7160 · CLASS 1.7

16MnCrB5

Material no. 1.7160


Chemical composition, mechanical and physical property values, and 1 standard designations from 1 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.76 g/cm³	1 in 1 regions	8 on file


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Mechanical properties

5 values across 5 conditions

SOFT ANNEALED	HB
Soft annealed	207
TREATED TO HARDNESS RANGE	HB
Treated to hardness range	156–207
TREATED TO FERRITE-PEARLITE STRUCTURE AND HARDNESS RANGE	HB
Treated to ferrite-pearlite structure and hardness range	140–187
NORMALIZED	HB
Normalized	138–187
CONDITION · DIMENSION	RM N/mm²
200	1000

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.76	g/cm³

Designations across standards

1 designations · 1 documented as identical

Europe	1
16MnCrB5 This grade's own name	din-en

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 16MnCrB5

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.7160	Aug 20, 2026