

MATERIAL NUMBER 1.7003 · CLASS 1.7

38Cr2

Material no. 1.7003

Chemical composition, mechanical and physical property values, and 8 standard designations from 6 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.85 g/cm ³	8 in 6 regions	7 on file


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Mechanical properties

2 values across 2 conditions

TREATED TO IMPROVE SHEARABILITY	HB
Treated to improve shearability	255
SOFT ANNEALED	HB
Soft annealed	207

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

8 designations · 1 documented as identical

United States	2	Spain	1
G51400	uns	38 Cr 3	une
5140	aisi-sae	Italy	1
France	2	38Cr2	uni
38C2	afnor	Serbia	1
38Cr5	afnor	Č.4132	srps
Europe	1		
38Cr2	This grade's own name	din-en	

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 38Cr2

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.7003	Aug 20, 2026