

MATERIAL NUMBER 1.2004 · CLASS 1.2

85Cr1

Material no. 1.2004


Chemical composition, mechanical and physical property values, and 9 standard designations from 9 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 9 in 9 regions	PROPERTY VALUES 7 on file
--	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

9 designations · 1 documented as identical

Europe	1	Russia / CIS	1
85Cr1 This grade's own name	din-en	85	gost
United States	1	Czechia	1
1086	aisi-sae	12 090	csn
United Kingdom	1	Slovakia	1
CS80	bs	12090	stn
France	1	Poland	1
XC85	afnor	gat. 85	pn
International	1		
CS85	iso		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 85Cr1

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.2004	Aug 20, 2026