

MATERIAL NUMBER 1.0415 · CLASS 1.0

C26D

Material no. 1.0415


Chemical composition, mechanical and physical property values, and 8 standard designations from 6 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 8 in 6 regions	PROPERTY VALUES 11 on file
------------------------------	---	--------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element’s raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 800 °C	PREDICTED AE1 719 °C	PREDICTED ACM 493 °C	PREDICTED BS 580 °C
--------------------------------	--------------------------------	--------------------------------	-------------------------------

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

8 designations · 4 documented as identical

Europe	2	International	1
C26D This grade's own name	din-en	C25 C25E4 C25M2	iso
D 25-2 This grade's own name	din-en		
		Japan	1
United States	2	S25C	jis
G10250 This grade's own name	uns		
1025 This grade's own name	aisi-sae	China	1
		25	gb
United Kingdom	1		
C25 C25E C25R	bs		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about C26D

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.0415	Aug 20, 2026