

MATERIAL NUMBER 1.0511 · CLASS 1.0

# C40


## Material no. 1.0511

Chemical composition, mechanical and physical property values, and 63 standard designations from 21 regions.

|                              |                                               |                                     |
|------------------------------|-----------------------------------------------|-------------------------------------|
| DENSITY<br><b>7.85</b> g/cm³ | OTHER DESIGNATIONS<br><b>63</b> in 21 regions | PROPERTY VALUES<br><b>9</b> on file |
|------------------------------|-----------------------------------------------|-------------------------------------|

Chemical composition

Mass fraction in %



Predicted transformation temperatures

computed from composition · °C

|                                |                                |                                |                               |
|--------------------------------|--------------------------------|--------------------------------|-------------------------------|
| PREDICTED AE3<br><b>774</b> °C | PREDICTED AE1<br><b>724</b> °C | PREDICTED ACM<br><b>603</b> °C | PREDICTED BS<br><b>560</b> °C |
|--------------------------------|--------------------------------|--------------------------------|-------------------------------|

Mechanical properties

17 values across 3 conditions

| COLD DRAWN / HARD    | RM<br>N/mm <sup>2</sup> | A<br>% |
|----------------------|-------------------------|--------|
| 5 – 10               | 700–1000                | 6      |
| 10 – 16              | 650–980                 | 7      |
| 16 – 40              | 620–920                 | 8      |
| 40 – 63              | 590–840                 | 9      |
| 63 – 100             | 550–820                 | 9      |
| NORMALIZED           | RM<br>N/mm <sup>2</sup> | A<br>% |
| ≤ 16                 | 580                     | 16     |
| 16 – 100             | 550                     | 17     |
| 100 – 250            | 530                     | 17     |
| AS ROLLED AND TURNED | HB                      |        |
| As rolled and turned | 163–211                 |        |

Physical properties

1 values

| PROPERTY | VALUE | UNIT              |
|----------|-------|-------------------|
| Density  | 7.85  | g/cm <sup>3</sup> |

Designations across standards

63 designations · 3 documented as identical

| France  |       | 12 | United Kingdom |                       | 8        |
|---------|-------|----|----------------|-----------------------|----------|
| 2C40    | afnor |    | 060A40         |                       | bs       |
| AF60C40 | afnor |    | 070M40         |                       | bs       |
| AF60C45 | afnor |    | 080A40         |                       | bs       |
| C40E    | afnor |    | 080M40         |                       | bs       |
| CC40    | afnor |    | C40            |                       | bs       |
| FR38    | afnor |    | C40E           |                       | bs       |
| XC 42   | afnor |    | CS40           |                       | bs       |
| XC3841  | afnor |    | En8            |                       | bs       |
| XC38H1  | afnor |    | United States  |                       | 6        |
| XC42H1  | afnor |    | G10400         | This grade's own name | uns      |
| XC42HI  | afnor |    | 1038           |                       | aisi-sae |
| XP42HI  | afnor |    | 1040           | This grade's own name | aisi-sae |
|         |       |    | 1042           |                       | aisi-sae |
|         |       |    | G10400         |                       | aisi-sae |
|         |       |    | G10420         |                       | aisi-sae |

|                                        |        |                                |        |
|----------------------------------------|--------|--------------------------------|--------|
| <b>Poland</b>                          | 5      | <b>Russia / CIS</b>            | 2      |
| 40                                     | pn     | 40                             | gost   |
| 40A                                    | pn     | ст.40                          | gost   |
| 40rs                                   | pn     |                                |        |
| D40                                    | pn     | <b>Sweden</b>                  | 2      |
| P40                                    | pn     | 1555                           | ss     |
|                                        |        | 1650                           | ss     |
| <b>Japan</b>                           | 4      |                                |        |
| S 40C                                  | jis    | <b>Australia / New Zealand</b> | 2      |
| S43C                                   | jis    | 1040                           | as-nzs |
| SWRCH38K                               | jis    | M1040                          | as-nzs |
| SWRCH40K                               | jis    |                                |        |
| <b>Europe</b>                          | 3      | <b>Romania</b>                 | 2      |
| 1.0511                                 | din-en | OLC40                          | stas   |
| C40 <span>This grade's own name</span> | din-en | OLC40X                         | stas   |
| Ck40                                   | din-en |                                |        |
| <b>Italy</b>                           | 3      | <b>Bulgaria</b>                | 2      |
| C40                                    | uni    | 40                             | bds    |
| C40E                                   | uni    | C40E                           | bds    |
| C40R                                   | uni    |                                |        |
| <b>Spain</b>                           | 2      | <b>Czechia</b>                 | 1      |
| C40E                                   | une    | 12041                          | csn    |
| F.114.A                                | une    |                                |        |
| <b>International</b>                   | 2      | <b>Slovakia</b>                | 1      |
| C40                                    | iso    | 12 041                         | stn    |
| C40E4                                  | iso    |                                |        |
| <b>China</b>                           | 2      | <b>Serbia</b>                  | 1      |
| 40                                     | gb     | Č.1540                         | srps   |
| ML40                                   | gb     |                                |        |
|                                        |        | <b>Hungary</b>                 | 1      |
|                                        |        | C40E                           | msz    |
|                                        |        | <b>Belgium</b>                 | 1      |
|                                        |        | C40-2                          | nbn    |
|                                        |        |                                |        |
|                                        |        | <b>South Korea</b>             | 1      |
|                                        |        | SM40C                          | ks     |

**Note on use.** The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

## Enquiry about C40

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

### DATASHEET ONLINE

View the material page

### GRADE SEARCH

Search all grades

### MATERIAL NO.

1.0511

### ISSUED

Aug 20, 2026