

MATERIAL NUMBER 5.5604 · CLASS 5.5

EN-GJN-HV550

Material no. 5.5604

also listed as EN-GJN-HB510

Chemical composition, mechanical and physical property values, and 4 standard designations from 2 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.85 g/cm ³	4 in 2 regions	9 on file

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 86.3 % ● Ni — 4.2 % ● C — 3.3 % ● Cr — 2.7 % ● Traces & impurities · 3.6 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

4 designations · 4 documented as identical

Europe	3	United States	1
EN-GJN-HB510	This grade's own name din-en	F45000	This grade's own name uns
EN-GJN-HV550	This grade's own name din-en		
G-X 330 NiCr 4 2	This grade's own name din-en		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about EN-GJN-HV550

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	5.5604	Aug 20, 2026