

MATERIAL NUMBER 1.1230 · CLASS 1.1

Federstahlstahldraht FD

Material no. 1.1230


also listed as C65S1

Chemical composition, mechanical and physical property values, and 6 standard designations from 2 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 6 in 2 regions	PROPERTY VALUES 8 on file
------------------------------	---	-------------------------------------

Chemical composition

Mass fraction in %



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

6 designations · 6 documented as identical

United States		4	Europe		2
G10650	This grade's own name	uns	C65S1	This grade's own name	din-en
K07001	This grade's own name	uns	Federstahlstahldraht FD	This grade's own name	din-en
1065	This grade's own name	aisi-sae			
J3161994	This grade's own name	aisi-sae			

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about Federstahlstahldraht FD

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.1230	Aug 20, 2026