

MATERIAL NUMBER 1.0455 · CLASS 1.0

GS 240


Material no. 1.0455

Chemical composition, mechanical and physical property values, and 5 standard designations from 3 regions.


DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 5 in 3 regions	PROPERTY VALUES 11 on file
--	---	--------------------------------------

Chemical composition

Mass fraction in %



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element’s raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 816 °C	PREDICTED AE1 721 °C	PREDICTED ACM 460 °C	PREDICTED BS 561 °C
--------------------------------	--------------------------------	--------------------------------	-------------------------------

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

5 designations · 1 documented as identical

Europe	2	China	2
GS 240	This grade's own name din-en	ZG230-450	gb
ZGD270-480	din-en	ZGD270-480	gb
		Czechia	1
		11474	csn

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about GS 240

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.0455	Aug 20, 2026