

MATERIAL NUMBER 1.4729 · CLASS 1.4

GX40CrSi13

Material no. 1.4729


Chemical composition, mechanical and physical property values, and 6 standard designations from 3 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 6 in 3 regions	PROPERTY VALUES 9 on file
--	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Mechanical properties

1 values across 1 conditions

SOFT ANNEALED	HB
Soft annealed	300

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

6 designations · 2 documented as identical

Japan	3	United States	2
SCH 1	jis	J91153 This grade's own name	uns
SCH 1X	jis	J91153	aisi-sae
SCH 3	jis		
		Europe	1
		GX40CrSi13 This grade's own name	din-en

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about GX40CrSi13

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.4729	Aug 20, 2026