

MATERIAL NUMBER 1.8972 · CLASS 1.8

L415NE

Material no. 1.8972

also listed as L415NB


Chemical composition, mechanical and physical property values, and 6 standard designations from 2 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 6 in 2 regions	PROPERTY VALUES 15 on file
--	---	--------------------------------------

Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 809 °C	PREDICTED AE1 713 °C	PREDICTED ACM 445 °C	PREDICTED BS 550 °C
-------------------------	-------------------------	-------------------------	------------------------

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

6 designations · 2 documented as identical

Europe	4	United States	2
1.8972	din-en	X60	aisi-sae
L415NB This grade's own name	din-en	A 860 Grade WPHY60	astm
L415NE	din-en		
StE 415.7 This grade's own name	din-en		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about L415NE

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.8972	Aug 20, 2026