SteelEquivalents.com

Material datasheet
As of Aug 20, 2026

MATERIAL NUMBER 1.8887 · CLASS 1.8

S460G2+QT

Material no. 1.8887

also listed as S460G2+M

Chemical composition, mechanical and physical property values, and 9 standard designations from 4 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.85 g/cm³	9 in 4 regions	15 on file

Chemical composition

Mass fraction in %

What this alloy is

Iron — the balance, never listed by a standard — 96.1 % · Mn — 1.7 % · Ni — 0.7 % · Si — 0.4 % · Traces & impurities · 1.2 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3	PREDICTED AE1	PREDICTED ACM	PREDICTED BS
818 °C	708 °C	385 °C	542 °C

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

9 designations · 2 documented as identical

Europe 4

2YGr.60	din-en
S460G2	din-en
S460G2+M This grade's own name	din-en
S460G2+QT This grade's own name	din-en

United States 2

2WGr.60	aisi-sae
2YGr.60	aisi-sae

Norway 2

Y40S460M3z	ns
Y40S460Q3z	ns

United Kingdom 1

450EMZ	bs

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.8887	Aug 20, 2026