

MATERIAL NUMBER 1.8991 · CLASS 1.8

S550A

Material no. 1.8991


Chemical composition, mechanical and physical property values, and 1 standard designations from 1 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 1 in 1 regions	PROPERTY VALUES 15 on file
------------------------------	---	--------------------------------------

Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 794 °C	PREDICTED AE1 687 °C	PREDICTED ACM 366 °C	PREDICTED BS 506 °C
-------------------------	-------------------------	-------------------------	------------------------

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

1 designations · 1 documented as identical

Europe	1
S550A This grade's own name	din-en

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about S550A

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.8991

ISSUED

Aug 20, 2026