

MATERIAL NUMBER 1.8986 · CLASS 1.8

S550QL1

Material no. 1.8986


also listed as EStE 550 V

Chemical composition, mechanical and physical property values, and 2 standard designations from 1 regions.


DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 2 in 1 regions	PROPERTY VALUES 16 on file
------------------------------	---	--------------------------------------

Chemical composition

Mass fraction in %



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

computed from composition · °C

PREDICTED AE3 792 °C	PREDICTED AE1 723 °C	PREDICTED ACM 475 °C	PREDICTED BS 456 °C
-------------------------	-------------------------	-------------------------	------------------------

Mechanical properties

5 values across 1 conditions

CONDITION · DIMENSION	REH N/mm²	RM N/mm²
3 – 100	–	640–820
3 – 50	550	–
50 – 100	530	–
100 – 150	490	590–770

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

2 designations · 2 documented as identical

Europe	2
ESTe 550 V This grade's own name	din-en
S550QL1 This grade's own name	din-en

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about S550QL1

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE View the material page	GRADE SEARCH Search all grades	MATERIAL NO. 1.8986	ISSUED Aug 20, 2026
--	-----------------------------------	------------------------	------------------------