

MATERIAL NUMBER 1.9416 · CLASS 1.9

SAE 1030


Material no. 1.9416

Chemical composition, mechanical and physical property values, and 9 standard designations from 7 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 9 in 7 regions	PROPERTY VALUES 5 on file
------------------------------	---	-------------------------------------

Chemical composition

Mass fraction in %



The scale is logarithmic, not the element’s raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Si, Ni, Cr, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

9 designations · 3 documented as identical

United States	2	France	1
G10300	This grade's own name uns	XC32	afnor
1030	This grade's own name aisi-sae		
United Kingdom	2	International	1
060A30	bs	C30 C30E4 C30M2	iso
C30 C30E C30R	bs		
Europe	1	Japan	1
SAE 1030	This grade's own name din-en	S30C	jis
		China	1
		30	gb

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about SAE 1030

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.9416	Aug 20, 2026