

MATERIAL NUMBER 1.0130 · CLASS 1.0

SPH 265

Material no. 1.0130

also listed as P265S


Chemical composition, mechanical and physical property values, and 6 standard designations from 5 regions.

DENSITY 7.85 g/cm ³	OTHER DESIGNATIONS 6 in 5 regions	PROPERTY VALUES 7 on file
--	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

7 values across 1 conditions

NORMALIZED	REH N/mm ²	A %
2 – 2.5	–	17
2.5 – 3	–	18
3 – 40	–	22
≤ 16	265	–
16 – 40	255	–
40 – 60	245	22

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

6 designations · 2 documented as identical

Europe	2	France	1
P265S This grade's own name	din-en	A42AP	afnor
SPH 265 This grade's own name	din-en		
		Spain	1
United Kingdom	1	SPH265	une
164-400B-LT20	bs		
		Italy	1
		Fe410-2KW	uni

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about SPH 265

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

1.0130

ISSUED

Aug 20, 2026