

MATERIAL NUMBER 1.0037 · CLASS 1.0

St 37-2 G

Material no. 1.0037

also listed as S235JR+CR

Chemical composition, mechanical and physical property values, and 10 standard designations from 4 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 10 in 4 regions	PROPERTY VALUES 5 on file
------------------------------	--	-------------------------------------

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 99.7 % ● C — 0.2 % ● P — 0 % ● S — 0 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mn, Si, Ni, Cr, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

10 designations · 5 documented as identical

United States		5	Europe		2
G10150	This grade's own name	uns	S235JR+CR	This grade's own name	din-en
K02401	This grade's own name	uns	St 37-2 G	This grade's own name	din-en
1015	This grade's own name	aisi-sae	Poland		2
A283 Gr.C		aisi-sae	St3S		pn
A573		aisi-sae	St3SX		pn
			Serbia		1
			Č.0363		srps

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about St 37-2 G

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.0037	Aug 20, 2026