

MATERIAL NUMBER 1.2453 · CLASS 1.2

X130W5

Material no. 1.2453


Chemical composition, mechanical and physical property values, and 8 standard designations from 6 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.85 g/cm³	8 in 6 regions	11 on file

Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Mechanical properties

1 values across 1 conditions

CONDITION · DIMENSION	HB
(annealing)	255

Physical properties

4 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³
Transformation point Ac1	750	°C

Technological properties

PROPERTY	VALUE	UNIT
Weldability	is not used.	
Temper brittleness	weakly predisposed	

Designations across standards

8 designations · 1 documented as identical

Russia / CIS	2	United States	1
KHV4F	gost	F2	aisi-sae
XB4Φ	gost		
Czechia	2	Japan	1
19 XXX NN	csn	SKS11	jis
19714	csn	Austria	1
Europe	1	K400	onorm
X130W5	This grade's own name	din-en	

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about X130W5

Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.2453	Aug 20, 2026