

MATERIAL NUMBER 1.4434 · CLASS 1.4

X2CrNiMoN18-12-4

Material no. 1.4434


Chemical composition, mechanical and physical property values, and 8 standard designations from 4 regions.

DENSITY	OTHER DESIGNATIONS	PROPERTY VALUES
7.85 g/cm ³	8 in 4 regions	10 on file


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Mechanical properties

6 values across 1 conditions

CONDITION · DIMENSION	RM N/mm²	RE N/mm²	A %	HB	HRB	HV
Plate/Sheet Hot-rolled	550	245	40	–	–	–
Hot-rolled	–	–	–	217	95	220

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm³

Designations across standards

8 designations · 3 documented as identical

United States	5	Europe	1
S31726	uns	X2CrNiMoN18-12-4	This grade's own name din-en
S31753	This grade's own name uns		
317LMN	aisi-sae	France	1
317LN	This grade's own name aisi-sae	Z3CND18-14-05Az	afnor
S31753	aisi-sae	Japan	1
		SUS317LN	jis

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about X2CrNiMoN18-12-4

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.4434	Aug 20, 2026