

MATERIAL NUMBER 1.4015 · CLASS 1.4

X8Cr18

Material no. 1.4015


Chemical composition, mechanical and physical property values, and 7 standard designations from 6 regions.

DENSITY 7.7 g/cm ³	OTHER DESIGNATIONS 7 in 6 regions	PROPERTY VALUES 7 on file
---	---	-------------------------------------


Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.7	g/cm ³

Designations across standards

7 designations · 2 documented as identical

United States		2	Czechia		1
S43080	This grade's own name	uns	17031		csn
430		aisi-sae			
Europe		1	Slovakia		1
X8Cr18	This grade's own name	din-en	17 031		stn
Russia / CIS		1	Poland		1
12Ch17		gost	H17		pn

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about X8Cr18

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.4015	Aug 20, 2026