

MATERIAL NUMBER 1.0543 · CLASS 1.0

ZSt 60-2

Material no. 1.0543

also listed as E335GC

Chemical composition, mechanical and physical property values, and 6 standard designations from 3 regions.

DENSITY 7.85 g/cm³	OTHER DESIGNATIONS 6 in 3 regions	PROPERTY VALUES 4 on file
------------------------------	---	-------------------------------------

Chemical composition

Mass fraction in %

What this alloy is



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element’s raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: C, Mn, Si, Ni, Cr, Mo.

Mechanical properties

11 values across 2 conditions

COLD DRAWN / HARD	RM N/mm²	A %
5 – 10	700–1050	5
10 – 16	680–970	6

COLD DRAWN / HARD	RM N/mm ²	A %
16 – 40	640–930	7
40 – 63	620–870	8
63 – 100	570–810	8
AS ROLLED AND TURNED		HB
As rolled and turned		169–211

Physical properties

1 values

PROPERTY	VALUE	UNIT
Density	7.85	g/cm ³

Designations across standards

6 designations · 2 documented as identical

Europe		4	France		1
E335GC	This grade's own name	din-en	A60-2		afnor
Fe590-2		din-en			
St60-2		din-en	Italy		1
ZSt 60-2	This grade's own name	din-en	Fe590		uni

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about ZSt 60-2

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	1.0543	Aug 20, 2026