


022Cr11Ti

Chemical composition, mechanical and physical property values, and 1 standard designations from 1 regions.


ELASTIC MODULUS 201 GPa	OTHER DESIGNATIONS 1 in 1 regions	PROPERTY VALUES 15 on file
-----------------------------------	---	--------------------------------------

Chemical composition

Mass fraction in %



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Physical properties

5 values

CONDITION · DIMENSION	E GPa	ALPHA 10 ⁻⁶ /K	LAMBDA W/(m·K)	CP J/(kg·K)
20	220	—	—	—
100	215	10.5	24.9	—
200	210	11	—	—
300	205	11.5	—	—
400	195	12	—	—
500	—	12	28.5	460

PROPERTY	VALUE	UNIT
Elastic modulus	201	GPa
Thermal expansion coefficient	10.6	10 ⁻⁶ /K
Thermal conductivity	25	W/(m·K)
Specific heat capacity	460	J/(kg·K)
Electrical resistivity	600	nΩ·m

Heat treatment

1 regimes

STEP	TEMPERATURE	MEDIUM
Annealing	Temperature not stated	—

Designations across standards

1 designations · 1 documented as identical

China	1
022Cr11Ti This grade's own name	gb

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 022Cr11Ti

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

—

ISSUED

Aug 15, 2026