

022Cr18Nb

Chemical composition, mechanical and physical property values, and 1 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
1 in 1 regions	10 on file

Chemical composition


Mass fraction in %

What this alloy is



Iron — the balance, never listed by a standard — 79.6 % Cr — 18 % Si — 1 % Mn — 1 % Traces & impurities · 0.4 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Mo.

Physical properties

3 values

CONDITION · DIMENSION	E GPa	ALPHA 10 ⁻⁶ /K
20	220	—

CONDITION · DIMENSION	E GPa	ALPHA 10^-6/K
100	215	10
200	210	10.5
300	205	10.5
400	195	10.5
500	—	11

PROPERTY	VALUE	UNIT
Thermal conductivity	25	W/(m·K)
Specific heat capacity	460	J/(kg·K)
Electrical resistivity	600	nΩ·m

Designations across standards

1 designations · 1 documented as identical

China	1
022Cr18Nb This grade's own name	gb

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 022Cr18Nb

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	—	Aug 15, 2026