

16Cr25Ni20Si2

Chemical composition, mechanical and physical property values, and 1 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
1 in 1 regions	10 on file

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 51.2 % ● Cr — 25.5 % ● Ni — 19.5 % ● Si — 2 % ● Traces & impurities · 1.8 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Physical properties

3 values

CONDITION · DIMENSION		ALPHA 10 ⁻⁶ /K	
200		15.5	
400		17.5	
PROPERTY	VALUE	UNIT	
Thermal conductivity	15	W/(m·K)	
Specific heat capacity	500	J/(kg·K)	
Electrical resistivity	900	nΩ·m	

Heat treatment

2 regimes

STEP	TEMPERATURE	MEDIUM
Solution annealing	Temperature not stated	—
Solution annealing	Temperature not stated	—

Designations across standards

1 designations · 1 documented as identical

China	1
16Cr25Ni20Si2 This grade's own name	gb

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 16Cr25Ni20Si2

[Start an enquiry](#)

Quotation, availability, mill certificate or a technical question — directly on the material page.

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

—

ISSUED

Aug 15, 2026