

21Cr12MoV

Chemical composition, mechanical and physical property values, and 1 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
1 in 1 regions	10 on file

Chemical composition


Mass fraction in %

What this alloy is



Iron — the balance, never listed by a standard — 85.1 % Cr — 11.8 % Mo — 1 % Mn — 0.6 % Traces & impurities · 1.6 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

This grade's composition falls outside the published model's validated range (a low-alloy composition window), so no transformation temperature is predicted here.

Heat treatment

3 regimes

STEP	TEMPERATURE	MEDIUM
multiple operations, source states neither order nor alternation		
Annealing	880–930 °C	—
Tempering	750–770 °C	—
source joins the operations with + / procedural order		
Quenching	1020–1050 °C	Oil
Tempering	700–750 °C	Air
source joins the operations with + / procedural order		
Quenching	1020–1070 °C	Oil
Tempering	650 °C	Air

Designations across standards

1 designations · 1 documented as identical

China	1
21Cr12MoV This grade's own name	gb

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 21Cr12MoV

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE View the material page	GRADE SEARCH Search all grades	MATERIAL NO. —	ISSUED Aug 15, 2026
---	--	--------------------------	-------------------------------