

30Cr13

Chemical composition, mechanical and physical property values, and 1 standard designations from 1 regions.

ELASTIC MODULUS 219 GPa	OTHER DESIGNATIONS 1 in 1 regions	PROPERTY VALUES 12 on file
-----------------------------------	---	--------------------------------------

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 84 % ● Cr — 13 % ● Si — 1 % ● Mn — 1 % ● Traces & impurities · 1 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Physical properties

5 values

CONDITION · DIMENSION	E GPa	ALPHA 10 ^{^-6} /K	LAMBDA W/(m·K)	CP J/(kg·K)
20	215	—	—	—

CONDITION · DIMENSION	E GPa	ALPHA 10 ⁻⁶ /K	LAMBDA W/(m·K)	CP J/(kg·K)
100	212	10.5	25.1	—
200	205	11	—	—
300	200	11.5	—	—
400	190	12	—	—
500	—	—	25.5	170

PROPERTY	VALUE	UNIT
Elastic modulus	219	GPa
Thermal expansion coefficient	10.5	10 ⁻⁶ /K
Thermal conductivity	30	W/(m·K)
Specific heat capacity	460	J/(kg·K)
Electrical resistivity	550	nΩ·m

Heat treatment

7 regimes

STEP	TEMPERATURE	MEDIUM
Annealing	Temperature not stated	—
Annealing	Temperature not stated	—
source joins the operations with + / procedural order		
Quenching	Temperature not stated	—
Tempering	Temperature not stated	—
source joins the operations with + / procedural order		
Quenching	Temperature not stated	—
Solution annealing	1000–1050 °C	—
Tempering	Temperature not stated	—
Ageing	200–300 °C	Air
Quenching and tempering	Temperature not stated	—
Annealing	Temperature not stated	—
Annealing	750 °C	—

Designations across standards

1 designations · 1 documented as identical

China	1
30Cr13 This grade's own name	gb

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 30Cr13
Quotation, availability, mill certificate or a technical question — directly on the material page.

Start an enquiry

DATASHEET ONLINE
View the material page

GRADE SEARCH
Search all grades

MATERIAL NO.
—

ISSUED
Aug 15, 2026