

ML20Al


also listed as C20E2C

Chemical composition, mechanical and physical property values, and 5 standard designations from 5 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
5 in 5 regions	6 on file

Chemical composition

Mass fraction in %



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni, Cr, Mo.

Mechanical properties

6 values across 3 conditions

CONDITION · DIMENSION	RM N/mm²
≤ 12	≤ 530

CONDITION · DIMENSION			RM N/mm ²
≥ 12			≤ 530
CONDITION · DIMENSION	RM N/mm ²	RE N/mm ²	A %
25 – 25	520–820	≥ 320	≥ 11
CONDITION · DIMENSION			RM N/mm ²
/			≤ 490

Heat treatment

1 regimes

STEP	TEMPERATURE	MEDIUM
Annealing	Temperature not stated	—

Designations across standards

5 designations · 1 documented as identical

Europe	1	Japan	1
C20E2C	din-en	SWRCH20A	jis
United States	1	China	1
1020	astm	ML20AI This grade's own name	gb
International	1		
C20E2C	iso		

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about ML20AI

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE	GRADE SEARCH	MATERIAL NO.	ISSUED
View the material page	Search all grades	—	Aug 15, 2026