


W7Mo7Cr4V7Co11

Chemical composition, mechanical and physical property values, and 1 standard designations from 1 regions.


OTHER DESIGNATIONS	PROPERTY VALUES
1 in 1 regions	10 on file

Chemical composition

Mass fraction in %



Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element’s raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Ni.

Heat treatment

2 regimes

STEP	TEMPERATURE	MEDIUM
source joins the operations with + / procedural order		
Preheating	800–900 °C	—
Quenching	1160–1180 °C	—
Tempering	550 °C	—
Annealing	Temperature not stated	—

Designations across standards

1 designations · 1 documented as identical

China	1
W7Mo7Cr4V7Co11 This grade's own name	gb

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about W7Mo7Cr4V7Co11

Quotation, availability, mill certificate or a technical question — directly on the material page.

[Start an enquiry](#)

DATASHEET ONLINE View the material page	GRADE SEARCH Search all grades	MATERIAL NO. —	ISSUED Aug 15, 2026
---	--	--------------------------	-------------------------------