

000X18H12

Chemical composition, mechanical and physical property values, and 3 standard designations from 1 regions.

OTHER DESIGNATIONS	PROPERTY VALUES
3 in 1 regions	8 on file

Chemical composition


Mass fraction in %

What this alloy is



● Iron — the balance, never listed by a standard — 68.9 % ● Cr — 18 % ● Ni — 12.3 % ● Si — 0.4 % ● Traces & impurities · 0.5 %

Logarithmic scale, 0.01 % to 100 % — every value here compares directly, decade by decade.



The scale is logarithmic, not the element's raw share of the alloy — the only honest way to fit 0.01 % and 100 % in one picture, and it means every value here can be compared with every other.

Predicted transformation temperatures

Not enough recorded composition to predict a transformation temperature for this grade — missing: Mo.

Mechanical properties

6 values across 2 conditions

CONDITION · DIMENSION	RM N/mm ²	A5 %
Sheet thin, GOST 5582-75	740	12
Sheet thin, GOST 4986-79	740	3–5

CONDITION · DIMENSION	RM N/mm ²	A5 %
Sheet thin, GOST 5582-75	390	40

Designations across standards

3 designations · 1 documented as identical

Russia / CIS	3
000X18H12	gost
03KH18N12 This grade's own name	gost
03X18H12	gost

Note on use. The data is compiled to the best of our knowledge from publicly available standards and manufacturer documentation. It replaces neither material testing nor an inspection document to EN 10204. Please request a mill certificate to EN 10204 2.1, 3.1 or 3.2 together with your enquiry. The standard in its current valid edition always prevails.

Enquiry about 000X18H12

[Start an enquiry](#)

Quotation, availability, mill certificate or a technical question — directly on the material page.

DATASHEET ONLINE

View the material page

GRADE SEARCH

Search all grades

MATERIAL NO.

—

ISSUED

Aug 15, 2026